

# DEEP LEATHER

COLOR	MIXING	SPRAY BOTTLE SETTING	APPROXIMATE SURFACE COVERAGE	BEFORE NEXT STEP	TIME TO DO
CAPPUCCINO ACRYLIC CONCRETE STAIN	4 oz. to 4 oz. water	Mist	60%	1. Blot with rag to lift spots and puddles 2. While still wet begin next step	15 min.
CHARCOAL ACRYLIC CONCRETE STAIN	4 oz. to 4 oz. water	Mist	30-40%	1. Blot with rag as before 2. Lift out black spots	15 min.
CAPPUCCINO ACRYLIC CONCRETE STAIN	4 oz. to 4 oz. water	Mist	30%	1. Blot to hide spots or to lighten areas	15 min.

**SEAL THE NEXT DAY!**

