



GRANICRETE
INTERNATIONAL

Roasted Pepper



For this finish you will need:

1. Brick Red FX
2. Taupe-Dispersion
3. Blinding White – Acryli-Shade

Mixing Procedure:

1. Mix Brick Red FX (2 caps to 20oz of water) into a *Granicrete* professional spray bottle.
2. Mix Taupe (3 caps to 24oz of water) into a *Granicrete* professional *spray bottle*.
3. Mix Blinding White (4oz to 20oz of water) into a *Granicrete* professional *spray bottle*

Step-by-Step Procedure:

1. Apply all Granicrete Countertop Blend coats per installation instructions.
2. Stream and flood 100% of the surface using Brick Red FX. Allow to dry before proceeding.
3. Mist and speckle 20% of the surface using Taupe. Allow to dry before proceeding.
4. Mist and speckle 40% of the surface using Blinding White.
5. Allow surface to completely dry and then apply Granicrete Crystal Top Epoxy per product instructions.

Professional Tip: Constantly shake up FX colors while being used in a spray bottle. The powder within each FX color is what makes them unique. If the color rest in the spray bottle the powder will settle to the bottom.

Roasted Pepper Notes: