# Granicrete International

# Yellow Lake Waters



## For this finish you will need:
1. Slate Green-Dispersion
2. Burntwood Black – Acryli-Shade
3. Wickenburg White – Acryli-Shade
4. Blinding White – Acryli-Shade
5. Desert Brown – Acryli-Shade

## Mixing Procedure:
1. Mix Slate Green (2 caps to 24oz of water) into a *Granicrete* professional spray bottle.
2. Mix Burntwood Black (4oz to 24oz of water) into a *Granicrete* professional *spray bottle.*
3. Mix Wickenburg White (4oz to 24oz of water) into a *Granicrete* professional *spray bottle.*
4. Mix Blinding White (4oz to 24oz of water) into a *Granicrete* professional *spray bottle.*
5. Mix Desert Brown (4oz to 24oz of water) into a *Granicrete* professional *spray bottle.*

## Step-by-Step  Procedure:
1. Apply all Granicrete Countertop Blend coats per installation instructions.
2. Mist and speckle 90% of the surface using Slate Green.  While still wet, proceed.
3. Mist and speckle 40% of the surface using Burntwood Black. While still wet, proceed.
4. Mist and speckle 20% of the surface using Wickenburg White. Allow to dry before proceeding.
5. Steam and streak 80% of the surface using Blinding White. While still wet, proceed.
6. Stream and streak 40% of the surface using Burntwood Black. Allow to dry before proceeding.
7. Wide stream and streak 100% of the surface using water. Allow to dry before proceeding.
8. Mist and speckle 40% of the surface using Blinding White. While still wet, proceed.
9. Mist and speckle 40% of the surface using Burntwood Black. While still wet, proceed.
10. Mist and speckle 20% of the surface using Slate Green. Allow to dry before proceeding.
11. Mist and sponge (rub in) 50% of the surface using Desert Brown.
12. Allow surface to completely dry and then apply Granicrete Crystal Top Epoxy per product instructions.

**Professional Tip**:  Constantly shake up FX colors while being used in a spray bottle.  The powder within each FX color is what makes them unique.  If the color rest in the spray bottle the powder will settle to the bottom.